

DIMENSIONAL METAL

PRODUCT TYPE	SUBSTRATE	PRODUCT COLOR	VALSPAR ITEM CODE	INITIAL SOLAR REFLECTANCE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)
FLUROPON	GALVALUME	METALLIC SILVER	439RZ6415M	0.49	0.79	53
FLUROPON	GALVALUME	WEATHERED ZINC	439RZ6386M	0.36	0.83	37
FLUROPON	GALVALUME	BROWN	437R2609	0.26	0.86	25
FLUROPON	GALVALUME	DARK BRONZE	437R2377	0.28	0.86	27
FLUROPON	GALVALUME	ROYAL BLUE	436R2729	0.28	0.86	27
FLUROPON	GALVALUME	HEMLOCK GREEN	435R2215	0.31	0.86	31
FLUROPON	GALVALUME	LEAF GREEN	435R2214	0.31	0.86	31
FLUROPON	GALVALUME	COLONIAL RED	434R2068	0.33	0.86	34
FLUROPON	GALVALUME	PUTTY	433R2860	0.64	0.86	77
FLUROPON	GALVALUME	SANDSTONE	433R2859	0.64	0.86	77
FLUROPON	GALVALUME	BEIGE	433R2849	0.47	0.86	53
FLUROPON	GALVALUME	SLATE BLUE	436R2676	0.33	0.86	34
FLUROPON	GALVALUME	MUSKET GRAY	432R3265	0.33	0.87	35
FLUROPON	GALVALUME	SLATE GRAY	432R3253	0.42	0.87	47
FLUROPON	GALVALUME	DOVE GREY	432R3246	0.53	0.86	61
FLUROPON	GALVALUME	WHITE	431R1825	0.70	0.86	85
FLUROPON	GALVALUME	EVERGREEN	435R2258	0.28	0.87	28
FLUROPON	GALVALUME	CLASSIC BRONZE	437R2378	0.29	0.86	29

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371 SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed.

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.

DIMENSIONAL METAL

PRODUCT TYPE	SUBSTRATE	PRODUCT COLOR	VALSPAR ITEM CODE	INITIAL SOLAR REFLECTANCE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)
FLUROPON	GALVALUME	BURGUNDY	434R2100	0.33	0.86	34
FLUROPON	GALVALUME	HARTFORD GREEN	435R2255	0.27	0.86	26
FLUROPON	GALVALUME	COBALT BLUE	436B2945	0.23	0.85	20
FLUROPON	GALVALUME	SEAPORT	435R2250	0.34	0.86	35
FLUROPON	GALVALUME	SPARTAN BRONZE	437R2368	0.30	0.86	30
FLUROPON	GALVALUME	CHARCOAL GRAY	432R3742	0.30	0.87	31
FLUROPON	GALVALUME	MATTE BLACK	438R927	0.29	0.86	29
FLUROPON	GALVALUME	PATINA COPPER	435R2252	0.51	0.86	58
FLUROPON	GALVALUME	TERRA COTTA	434R2092	0.40	0.86	43
FLUROPON	GALVALUME	STONE	437R2369	0.44	0.86	49
FLUROPON	GALVALUME	BRITE RED	434R2095	0.40	0.87	44
FLUROPON	GALVALUME	METALLIC COPPER	439RZ6300M	0.44	0.86	49
FLUROPON	GALVALUME	CHAMPAGNE	439RZ6413M	0.45	0.87	51
FLUROPON	GALVALUME	AGED COPPER	439RZ7106M	0.40	0.84	43

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371 SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Laboratory and Exposure site are ISO 17025 Accredited, Laboratory is also EPA Accredited. Panels are unwashed.

The VALSPAR CORPORATION certifies these tests to be true and accurate and performed by our laboratory.