



**SHERWIN-WILLIAMS**  
Coil Coatings

# FLUROPON®


## CERTIFIED LABORATORY TEST REPORT

### ACCELERATED WEATHERING QUV-A

<b>TEST PROCEDURES:</b>	ACCELERATED WEATHERING 2000 HOURS QUV-A, 340 NM BULB ASTM D 4587, ASTM G 154
<b>PRODUCT TESTED:</b>	FLUROPON®
<b>TEST RESULTS:</b>	ACCEPTABLE
<b>FILM INTEGRITY:</b>	NO CRACKING, PEELING, BLISTERING LOSS OF ADHESION OF THE COATING
<b>CHALKING:</b>	CHALK RATING OF 8 OR BETTER ASTM D 4214, METHOD A
<b>COLOR CHANGE:</b>	NO MORE THAN 2 ΔE HUNTER UNITS PER ASTM D 2244
<b>LOCATION:</b>	THE SHERWIN-WILLIAMS COMPANY FT. MYERS, FLORIDA, USA

*Marlene Garrow* 05/30/2019  
 Marlene Garrow Date  
 Group Leader

*Alexander J. Nicol* 5/30/19  
 Alexander J. Nicol Date  
 Notary Public



Notary Public stamp with expiration date

The SHERWIN-WILLIAMS COMPANY certifies these tests to be true, accurate and performed by our laboratory.