




SHERWIN-WILLIAMS.
Coil Coatings

FLUROPON®

CERTIFIED LABORATORY TEST REPORT

ACCELERATED WEATHERING QUV-A


TEST PROCEDURES:	ACCELERATED WEATHERING 3000 HOURS QUV-A, 340 NM BULB ASTM D 4587, ASTM G 154
PRODUCT TESTED:	FLUROPON®
TEST RESULTS:	ACCEPTABLE
FILM INTEGRITY:	NO CRACKING, PEELING, BLISTERING LOSS OF ADHESION OF THE COATING
CHALKING:	CHALK RATING OF 8 OR BETTER ASTM D 4214, METHOD A
COLOR CHANGE:	NO MORE THAN 2 ΔE HUNTER UNITS PER ASTM D 2244
LOCATION:	THE SHERWIN-WILLIAMS COMPANY FT. MYERS, FLORIDA, USA


Marlene Garrow
Group Leader

05/30/2019
Date


Alexander J. Nicol
Notary Public

5/30/19
Date



Notary Public stamp with expiration date

The SHERWIN-WILLIAMS COMPANY certifies these tests to be true, accurate and performed by our laboratory.

03/19