



FLUROPON[®]
CERTIFIED LABORATORY
TEST REPORT
CHEMICAL POLLUTION

TEST PROCEDURES:

CHEMICAL SPOT TEST PER ASTM D 1308

PRODUCT TESTED:

VALSPAR FLUROPON[®]

SUBSTRATE:

HDG, GALVALUME OR ALUMINUM

TEST RESULTS:

10% hydrochloric acid solution -
24 hour test - no visible changes
20% hydrochloric acid solution -
18 hour test – no bleaching
20% sulfuric acid –
18 hour test – no bleaching
25% sodium hydroxide –
1 hour test – no color change, no blistering
20% muriatic acid – 15 minute test
No significant color change, no blistering

LOCATION:

THE VALSPAR CORPORATION
FT. MYERS, FLORIDA, USA

 04/15/14

Marlene Garrow - Ft. Myers
Valspar Corporation

Date

The VALSPAR CORPORATION certifies these test to be true and accurate and performed by our laboratory.

04/14