



SHERWIN-WILLIAMS.
Coil Coatings

FLUROPON®

CERTIFIED LABORATORY TEST REPORT

HUMIDITY

TEST PROCEDURES: 2000 HOURS, 100% HUMIDITY
ASTM D 2247

PRODUCT TESTED: FLUROPON®

SUBSTRATE: HDG OR GALVALUME

TEST RESULTS: ACCEPTABLE CORROSION


- FIELD 10
- CUT EDGE 10 (0 MM)
- UNCUT EDGE 10 (0 MM)

ACCEPTABLE BLISTERING PER ASTM D 714

LOCATION: THE SHERWIN-WILLIAMS COMPANY
FT. MYERS, FLORIDA, USA

Marlene Garrow 05/30/2019
Marlene Garrow Date
Group Leader

Alexander J. Nicol 5/30/19
Alexander J. Nicol Date
Notary Public



Notary Public stamp with expiration date

The SHERWIN-WILLIAMS COMPANY certifies these tests to be true, accurate and performed by our laboratory.