



SHERWIN-WILLIAMS.
Coil Coatings

FLUROPON®

CERTIFIED LABORATORY TEST REPORT

CORROSION - SALT SPRAY

TEST PROCEDURES:

SALT SPRAY – 2000 HOURS PER
ASTM B 117

PRODUCT TESTED:

FLUROPON®

SUBSTRATE:

HDG OR GALVALUME

TEST RESULTS:

ACCEPTABLE CORROSION
RATED PER ASTM D 1654

- FIELD* 8
- SCRIBE 4mm
- RUST (ASTM D 610) 10


*FIELD REFERENCE ASTM D 714
NO BLISTERING

LOCATION:

THE SHERWIN-WILLIAMS COMPANY
FT. MYERS, FLORIDA, USA

Marlene Garrow 05/30/2019
 Marlene Garrow Date
 Group Leader

Alexander J. Nicol 5/30/19
 Alexander J. Nicol Date
 Notary Public



Notary Public stamp with expiration date

The SHERWIN-WILLIAMS COMPANY certifies these tests to be true, accurate and performed by our laboratory.