

FLUROPON®

CERTIFIED LABORATORY TEST REPORT

WEATHEROMETER

TEST PROCEDURES:

2000 HOURS ASTM D 822, ASTM G 152, ASTM G 153 – CARBON ARC WEATHERING

INSTRUMENT

PRODUCT TESTED:

FLUROPON®

TEST RESULTS:

ACCEPTABLE

FILM INTEGRITY:

NO CHECKING, BLISTERING, OR LOSS OF ADHESION

LOCATION:

THE SHERWIN-WILLIAMS COMPANY

FT. MYERS, FLORIDA, USA

Karlene Sarrow 05/30/2019

Marlene Garrow Group Leader

Date

Alexander J. Nicol Notary Public Date

ALEXANDER J. NICOL State of Florida-Notary Public Commission # GG 240196 My Commission Expires July 19, 2022

Notary Public stamp with expiration date